

# UPM Raflatac Technical Information

31.08.2016 ENG 1161

<b>Product</b>		<b>PP CLEAR FTC 50 / RP37 / HD 70 WHITE</b>	
Sales Code	DBH/RP37/28		
EAN	6415788236543		
Product use	Multi-purpose product for rigid containers, both polar and non-polar, where good water, chemical and oil resistance is needed. The high transparency of the face offers a good no-label look. The product complies with EU regulations on food safety.		
<b>Face</b>		<b>PP CLEAR FTC 50</b>	
Product	A transparent, glossy, biaxially oriented, top-coated polypropylene film.		
Substance	47	g/m <sup>2</sup>	ISO 536
Caliper	51	µm	ISO 534
Tensile strength MD	150.0	N/mm <sup>2</sup>	DIN 53455
Tensile strength CD	250.0	N/mm <sup>2</sup>	DIN 53455
Gloss	80	%	DIN 67530/2
Printability	Suitable for flexography, screen and offset printing methods. Special inks designed for non-absorbent materials should be used. Thermal transfer is possible with selected wax-resin and resin ribbons.		
<b>Adhesive</b>		<b>RP37</b>	
Type	Clear permanent adhesive.		
Composition	Acrylic, water borne.		
Tack min	9	N/25mm	FTM 9
Peel 90°	7	N/25mm	FTM 2
<b>Backing</b>		<b>HD 70 WHITE</b>	
Product	White transparent glassine backing paper.		
Substance	61	g/m <sup>2</sup>	ISO 536
Caliper	54	µm	ISO 534
Tensile strength MD	7.0	kN/m	ISO 1924
Tensile strength CD	2.6	kN/m	ISO 1924
Transparency	51	%	DIN 53147
<b>Performance</b>			
Total caliper	123 µm		
Minimum labelling temperature	5 °C		
Service temperature	-20 °C to 100 °C		
Shelf life	From the date of manufacture: 2 years at +20 °C and RH 50%. Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.		
<b>Approvals</b>			
Approvals & Certifications	Please see the individual Declaration of Conformance (DoC) document of each product component for further compliance information.		



**Disclaimer**

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

**UPM**

[www.upmraflatac.com](http://www.upmraflatac.com)